Connecting People, Science and Regulation

POLYMERS 101 – GLASS 101

PDA WORKSHOP
EXTRACTABLES – LEACHABLES

Brussels
13-14 March, 2014

Dr. Piet Christiaens

CONTENT

Content

1. What is a Polymer?
2. Classification of Polymers
3. Types of Polymers – Examples in Medical Use
4. Properties of polymers
5. Understanding the Composition of Polymers

WHAT IS A POLYMER?

Polymers 101

1. What is a “Polymer”?

*A **polymer** is a chemical compound or mixture of compounds consisting of repeating structural units created through a process of polymerization*

Greek words:
πολύς (polus, meaning "many, much")
μέρος (meros, meaning "parts")

Refers to a molecule whose structure is composed of multiple repeating units, from which originates a characteristic of high relative molecular mass and attendant properties.

NATURAL VS SYNTHETIC POLYMERS

Classification of Polymers

- Polymers also exist in Nature: **NATURAL POLYMERS**
  - Latex / Natural Rubber



  - Starch
  - Cellulose



  - Pectin



  - DNA



  - Silk / Wool
  - ....

- However, most of the Pharmaceutical Applications are with **SYNTHETIC POLYMERS**

SYNTHETIC Polymers

a small fraction are ***INORGANIC POLYMERS***

Example: Siloxanes (PolyDiMethylSiloxanes; PDMS) *(SILICONE)*



However, most of the Polymers are ***ORGANIC POLYMERS***

Examples: **see next slide**

SYNTHETIC Polymers

Some Examples of ***ORGANIC POLYMERS***



Polyethylene (PE)



nylon 6



nylon 6,6



Polypropylene





Ethylene Vinyl Acetate



IIR Rubber

Isobutyl **I**sopropenyl **R**ubber



THERMOPLASTIC VS THERMOSET POLYMERS

THERMOPLAST VERSUS THERMOSET





“Entangled” Polymer Chains

Crosslinked Polymer Chains

THERMOPLAST VERSUS THERMOSET

THERMOPLAST :

Polymers that soften when heated and become firm again when cooled

Examples: LDPE, HDPE, PP, PC, EVA,...

THERMOPLAST VERSUS THERMOSET

THERMOSET :

Polymers that soften when heated and molded subsequently

BUT

Decompose when Reheated

Thermoset polymers are typically "**cross linked**"

Example: Bakelite
Fenol Formaldehyde Resin

Rubbers

Silicone tubings

TYPES OF POLYMERS

TYPES OF POLYMERS - **HOMOPOLYMERS**

A-A-A-A-A-A-A-A-A-A-A-A-A-A-A-A

EXAMPLES:

- Polyethylene
- Polypropylene
- PVC

TYPES OF POLYMERS – **COPOLYMERS**

Random Copolymer A-B-A-A-B-B-B-A-B-A-A-A-B-A-B-B-A-B-A

Examples: Poly EVA



Regular Copolymer A-B-A-B-A-B-A-B-A-B-A-B-A-B-A-B-A-B-A

Examples:PET



Block Copolymer A-A-A-A-B-B-B-B-B-B-B-B-B-B-B-A-A-A-A

Examples



SIS Elastomer

TYPES OF POLYMERS – **CROSS-LINKED Polymers**



Isoprene/ Butadiene RUBBERS



Silicone rubbers (Pt-cured)



TYPES OF POLYMERS – **GRAFT COPOLYMERS**



graft copolymer

CLASSIFICATION BASED UPON POLYMERISATION MECHANISM

CHAIN GROWTH

Example 1: Cationic Polymerization of “Butyl Elastomer”

Lewis Acid



Example 2: Radical Polymerization of Polystyrene



STEP GROWTH (definition)



Examples: Polyaddition, polycondensation - PolyUrethane



POLYMER PROPERTIES

1. MORPHOLOGY

1. AMORPHOUS Polymers



Because of
- Irregularities in Polymer Structure
- The Nature of the Polymer
- Cross-linking (for certain Polymers)

No intermolecular bonds (e.g. Hydrogen bonds, Van der Waals forces) will lead to an alignment of the polymer chains

Examples: PS, PVC, SAN, ABS, PMMA, PC, PES

1. (Semi-)CRYSTALLINE POLYMERS



Hydrogen Bonds (e.g. PA)
Van der Waals Forces
(e.g. Polyolefins)

Bring “alignment” in chains





Kevlar



Nylon 6,6

AMORPHOUS versus CRYSTALLINE



AMORPHOUS versus CRYSTALLINE

Impact of **StereoChemistry** of a polymer on physical properties



Isotactic
Typically semi-crystalline
(e.g. PP via Ziegler-Natta polymerisation)



Syndiotactic
PS: Syndiotactic PS is semi-crystalline



Atactic
Typically amorphous polymers
PS: Atactic PS is amorphous

TACTICITY MODULATORS, SOMETIMES FOUND AS EXTRACTABLES

2. GLASS TRANSITION T° (T_g)

DEFINITION

GLASS TRANSITION TEMPERATURE (T_g):

Temperature when a Polymer goes from a “glassy” state ($< T_g$) to a “rubber” state ($> T_g$)

WHAT IS **RIGID** PACKAGING?



WHAT IS **FLEXIBLE** PACKAGING?



WHICH PACKAGING?



Mobility of chain segments in amorphous domains

- **Examples of T_g for different materials**

LDPE	**T_g = -125°C**
POM	**T_g = -50°C**
PP	**T_g = -25°C**
PBT	**T_g = +70°C**
PVC	**T_g = +81°C (non plasticized)**
ABS	**T_g = +110°C**
PC	**T_g = +150°C**

The T_g of a material will also have an impact on the migration behavior of a material!



Morphology is impacted by:

- Chain length
- Symmetry of Polymer
- Polarity of Polymer
- Chain Branching
- Flexibility/Rigidity of chains

COMPOSITION OF COMMERCIAL POLYMERS

COMPOSITION OF **COMMERCIAL POLYMERS**

- Additives
- Residues
- Oligomers
- Degradation Compounds from Polymers
- Degradation Compounds from Polymer Additives

1. ADDITIVES

Anti-Oxidants

Plasticizers

Photostabilizers

Slip Agents

Antiozonants

Coupling Agents

Lubricants

Acid Scavengers

Peroxides / Crosslinkers

Blowing Agents

Pigments/Colorants

Antistatic Agents

Metal Chelators

Adhesives

Bactericides

Clarifying Agents

Antifogging agents

Fillers

(Red: coming with some examples)

Anti-Oxidants

Function: assuring protection against thermal and oxidative degradation during processing and during shelf life of polymer
(*Sterically Hindered Phenols & Organic Phosphites/Phosphonates are mostly used*)

European Pharmacopoeia lists a.o. the following Anti-Oxidants:

BHT



Irganox 1010



Hostanox 03



Irganox 1330



Irgafos 168



Irganox 1076



Irganox 3114



Plasticizers

Function: Gives the plastic flexibility and durability
Plasticizer requirements:

- Low Water solubility (low extractibility)
- Stability to heat and light
- Low Odor, taste and toxicity

Diethylhexyladipate



Diethylhexylsebacate



TOTM



Diethylhexylphthalate (DEHP)



ESBO



Stearic Acid



Photostabilizers

Function: Protects the Polymer from UV-Degradation (exposure to sunlight)

Tinuvin 328



Tinuvin 770



Tinuvin 622



Slip Agents

Function: reduce the “friction” or “film adherence”, important when producing bags from films

Erucamide



Oleamide



Remark:
because of their specific properties, Slip agents will be widely detected as Leachables!

Acid Scavengers

Function: Protects the polymer from “acid attacks” through conversion of strong acids (high degradation impact) to weak acids (low degradation impact)

Examples: $Ca(Stearate)_2 + 2HCl \rightarrow CaCl_2 + Stearic\ acid$

strong acid *weak acid*



Pigments / Colorants

Function: Gives the polymer/rubber the desired color (cosmetic)

Examples: Carbon Black (PNA's!), TiO_2 (white), Fe_2O_3 (red), Pigment Green 07

Solvent Red



Solvent yellow 114



Solvent Green 03



Remarks: beware of the composition of the Masterbatch!

Clarifying Agents (Nucleating Agents)

Function: by controlling the crystallisation (nucleation) when cooling off PP, it becomes transparent.

NC-4



Millad 3988



2. RESIDUES

Residues from the production process (non-limitative)

Solvents

Cyclohexane



Hexane



DHN



MIBK



IPA

Monomers



Styrene



Caprolactam



Methyl methacrylate



Isoprene

Catalysts

Titanium
Zirkonium
Cobalt
Aluminum
...

3. OLIGOMERS


narrow molar mass distribution
broad molar mass distribution
W(log M) [-]
0
1
2
3
4
5
6
1*10 5
5*10 5
1*10 6
Molar Mass [Da]
PSS WinGPC Unity, Build 8073, LAB_DH2, Instance #2

OLIGOMERS

OLIGOMERS: Examples

PET



PBT



Nylon 6



Nylon 6.6



Butyl Rubber



Polyester adhesive



Other typical oligomers from Silicone, PP, PE, Adhesives ...

4. POLYMER DEGRADATION COMPOUNDS

Polymer degradation Compounds

Origin: Oxidative degradation of the polymers

(when the polymer is not properly stabilized via anti-oxidants)

Example of Polymer Degradation Compounds from **Polypropylene**



Acids



Aldehydes



Alcohols



Ketones



Polymer Fragments

5. POLYMER ADDITIVE DEGRADATION COMPOUNDS

Example Degradation of **Irganox 1010**

SMALL degradation Compounds



LARGE degradation Compounds



- EXAMPLE: Degradation of Irgafos 168

  (also other degradation compounds for Irgafos 168 are known)



PROCESSING OF POLYMERS

Examples: Making of single use materials: melt processed



extrusion: continu (eg tubes)



injection moulding: batch process (eg connectors, ports)

Name(s)	Formula	Monomer	Examples of Uses
Polyethylene low density (LDPE)	$–(CH_2\text{-}CH_2)_n–$	ethylene $CH_2=CH_2$	Films for bags, multilayer contact film
Polyethylene high density (HDPE)	$–(CH_2\text{-}CH_2)_n–$	ethylene $CH_2=CH_2$	Bottles, Caps
Polypropylene (PP) different grades	$–[CH_2\text{-}CH(CH_3)]_n–$	propylene $CH_2=CHCH_3$	Bottles, Caps
Poly(vinyl chloride) (PVC)	$–(CH_2\text{-}CHCl)_n–$	vinyl chloride $CH_2=CHCl$	Bags, tubings
Polystyrene (PS)	$–[CH_2\text{-}CH(C_6H_5)]_n–$	styrene $CH_2=CHC_6H_5$	Secondary Packaging (Tubs)
Polytetrafluoroethylene (PTFE, Teflon)	$–(CF_2\text{-}CF_2)_n–$	tetrafluoroethylene $CF_2=CF_2$	Containers, seals, tubes, tubings, “inert”coatings…
Poly(methyl methacrylate) (PMMA)	$–[CH_2\text{-}C(CH_3)CO_2CH_3]_n–$	methyl methacrylate $CH_2=C(CH_3)CO_2CH_3$	Implantable Lenses (IOL)
Poly(vinyl acetate) (PVAc)	$–(CH_2\text{-}CHOCOCH_3)_n–$	vinyl acetate $CH_2=CHOCOCH_3$	Multilayer films
cis-Polyisoprene natural rubber	$–[CH_2\text{-}CH=C(CH_3)\text{-}CH_2]_n–$	isoprene $CH_2=CH\text{-}C(CH_3)=CH_2$	rubbers

TOXIKON

ADVANCING YOUR INNOVATION

GLASS 101

WORKSHOP
EXTRACTABLES - LEACHABLES

Dr. Piet Christiaens

Toxikon Europe NV

What is Glass?

An inorganic fused substance that has been cooled to a rigid condition without crystallization (e.g. Supercooled amorphous substance)

Why Glass as packaging material?

- Well-known material
- Transparent
- Heat resistant
- Good barrier properties: gas & vapour tight
- Chemically and physically (quite) inert.

J. Zuercher, ECA Course E/L, Prague 2010

Glass in Pharmaceutical Packaging

- Ampoules
- Injection Vials
- Infusion Bottles
- Syringes
- Carpules
- Bottles for oral drug products
- Bottles for solid preparations

J. Zuercher, ECA Course E/L, Prague 2010

Composition of Glass – Function of Ingredients

- SiO_2 : Backbone structure
- CaO : Increasing hardness & Chemical resistance
- Al_2O_3 : Increasing Chemical Resistance
- Na_2O & B_2O_3 : Lowering the melting point
- Fe_2O_3, TiO_2 : Amber Glass
- CuO : Blue Glass
- Mn^{3+} : Violet Glass

J. Zuercher, ECA Course E/L, Prague 2010

Glass Types

Glass Type	General Description	Uses
I	High resistant Borosilicate	Parenteral Preparations
II	Treated Soda-Lime	Acidic and Neutral Parenteral Preparations
III	Soda Lime	Not for Parenteral Preparations
NP	Soda-Lime	Oral / Topical

Glass Composition for different Glass Types:

Component	Type I (Borosilicate)	Type II, III, NP (Soda-Lime)
SiO_2	70 - 73%	69 - 73%
B_2O_3	10%	0 - 1%
Na_2O	2 - 9%	13 - 14%
Al_2O_3	6 - 7%	2 - 4%
BaO	0,1 - 2,0%	0 - 2%
K_2O	1 - 2%	0 - 3%
CaO	0,7 - 1,0%	5 - 7%
MgO	0 - 0,5%	3 - 4%
ZnO	0 - 0,5%	-

Metal Profile of a Type I - Clear Glass Vial (ICP-MS)

Main Metals	Amount (%)	**Trace Metals (> 1µg/g)**	Amount (µg/g)
Si	>30%	Mg	61
Al	2%	Ba	21
Na	2,40%	Ce	8,8
B	5,50%	Ti	6,7
K	0,1%	Hf	6
Ca	0,036%	Mo	4,8
Fe	0,7 - 1,0%	Y	2,8
Zr	0 - 0,5%	La	2,5
		Sr	1,7
		Pd	1,6
		Ga	1,2
		Pb	1

Zuccarello et. Al., PDA, J Parm Sci technol 63, 339-352, 2009

Examples for Extractables / Leachables

- **High heating** during molding process leads to an **increasing release of alkali ions** from the glass surface => Delamination
- During the process, **components of the heated glass vaporize and deposit** on the surface
- **Heating promotes migration of alkali oxides** within the silica matrix to the glass surface
- Relevant for **glass containers** made from **tubular glass**
- **Small volume** containers are **more impacted** than larger containers

J. Zuercher, ECA Course E/L, Prague 2010

Parameters, impacting the Glass Leachables

- **Filling Volume**: *smaller filling volumes show higher leachable concentrations*
- **Storage time**: *leachable concentrations increase over time*
- **Sterilization / Sterilization time**: *longer autoclaving cycles, higher concentrations*
- **Sterilization Temperature**: *higher temperatures, higher concentrations*
- **Type of contact solution**:

  [Si]: Lactic acid < acetic acid < ascorbic acid < malic acid < tartaric acid < oxalic acid < citric acid

  ***Complexing agents**, such as EDTA may also impact the metal release from Glass*
- **Impact of pH**: *higher pH, higher [Si] release.*

  In general, more metals are leaching out of glass at pH>9

Risk of Glass Leachables

- **Most observed Metal Leachables from Glass:**
  Si and **Na** as MAJOR leachables, **K, B, Ca & Al** as MINOR LEA, **Fe**: traces
- **Alkali release:** pH shift of unbuffered solutions
- **Silicon (Si) release**:increased particle load, delamination!
- **Aluminum release**:
  Aluminum can accumulate in patients with reduced renal function, causing e.g. neurological diseases
- Potential **Arsenic (As) release**:
  glass can contain arsenic oxide (III) as a fining agent to improve glass tranparency. Arsenic is toxic!
- **Release of metals**, causing precipitation with some salts, present in the DP
  Ba => $BaSO_4$, Al => $Al(OH)_3$

How to (try to) prevent Glass Leaching

1. Chemical surface treatment

$(NH_4)SO_4$ is injected before annealing

$(NH_4)SO_4 \rightarrow (NH_4)HSO_4 + NH_3$

$2Na^+ + (NH_4)HSO_4 \rightarrow Na_2SO_4 + NH_3 + 2H^+$

Afterwards, rinsing with Water to remove soluble $NaSO_4$

Result: lower pH shift because lower amounts of Na will leach

How to (try to) prevent Glass Leaching

2. Put a Coating on the Glass

Deposition of SiO_x layer as an inert glass layer

e.g. Schott Type I Plus

How to (try to) prevent Glass Leaching

3. Siliconization

- Siliconized surfaces are hydrophobic, **reducing the wettability** of the container surface
- Thus siliconized glass surfaces are **reducing the potential of interactions** with aqueous fillings
- The **release of alkali ions is reduced**, compared to non-siliconized containers

However, Siliconized surface may then release organic compounds!

(e.g. Siloxanes)

ANY QUESTIONS?

For further questions, please contact:
piet.christiaens@toxikon.be

http://www.toxikon.be/extractables-leachables-parenteral-injectables.html